



HARDOX 500 SHEET



HARDOX 500 SHEET

General Product Description

The bendable, weldable and highly abrasion-resistant steel.

Hardox 500 is a bendable and weldable abrasion-resistant steel, with a nominal hardness of 500 HBW. Suitable for applications that demand higher wear resistance.

Hardox 500 increases payload and increases service life while maintaining good processability and toughness.

Dimension Range

Hardox 500 sheet are available in thicknesses 3.0- 6.5 mm. Hardox 500 Sheet is available in widths up to 1725 mm and lengths up to 16000 mm. More detailed information on dimensions is provided in the dimension program.

Mechanical Properties

Thickness (mm)	Hardness ¹⁾ (HBW)	Typical yield strength (MPa), not guaranteed
3.00- 6.50	470- 530	1400

¹⁾ Brinell hardness, HBW, according to EN ISO 6506-1, on a milled surface 0.5 – 3 mm below surface. At least one test specimen per heat and 40 tons.

Impact Properties

Grade	Longitudinal test, typical impact energy, Charpy V 10x10 mm test specimen.
Hardox 500	37 J /-40 °C

For thicknesses between 6 - 11.9 mm, subsize Charpy V-specimens are used. The specified toughness is then proportional to the cross-sectional area of the test specimen, compared to a full-size specimen (10 x 10 mm). Impact testing according to ISO EN 148 per heat and thickness group. Average of three tests.

Chemical Composition (heat analysis)

C ^{*)} (max %)	Si ^{*)} (max %)	Mn ^{*)} (max %)	P (max %)	S (max %)	Cr ^{*)} (max %)	Ni ^{*)} (max %)	Mo ^{*)} (max %)	B ^{*)} (max %)
0.27	0.50	1.60	0.025	0.010	1.20	0.25	0.25	0.005

The steel is grain refined. ^{*)} Intentional alloying elements.

HARDOX 500 SHEET

Carbon Equivalent CET (CEV)

Thickness (mm)	3.00 - 6.50
Max CET(CEV)	0.46 (0.58)
Typ CET(CEV)	0.40 (0.55)

$$CET = C + \frac{Mn + Mo}{10} + \frac{Cr + Cu}{20} + \frac{Ni}{40}$$

$$CEV = C + \frac{Mn}{6} + \frac{Cr + Mo + V}{5} + \frac{Cu + Ni}{15}$$

Tolerances

Thickness

Tolerances according to Hardox Thickness Guarantees. Hardox® Guarantees meets the requirements of ½ EN 10 051 for cut to length sheet.

Length and Width

According to SSAB's dimension program. Tolerances conform to EN 10 051. Tighter tolerances available on request.

Shape

Tolerances according to EN 10 051.

Flatness

For cut to length sheet the tolerances are according to Hardox Flatness Guarantees Class B, that offers narrower tolerances compared to EN 10 051.

Surface Properties

According to EN 10 163-2, Class A Subclass 1.

Bending

Tolerances for Hardox cut to length sheet are according to Hardox Bending Guarantees Class C.

Delivery Conditions

The delivery condition is Q (Quenched). Cut to length sheet are delivered with an as-rolled surface and mill edges as standard delivery condition. Delivery requirements can be found in SSAB's brochure 41-General Product Information Strenx, Hardox, Armox and Toolox-UK or at www.ssab.com.

Fabrication and Other Recommendations

Welding, bending and machining.

Recommendations can be found in SSAB's brochures at www.hardox.com or consult Tech Support, techsupport@ssab.com.

HARDOX 500 SHEET

Hardox 500 is not intended for further heat treatment. It has obtained its mechanical properties by quenching. The properties of the delivery condition cannot be retained after exposure to temperatures in excess of 250°C. Hardox sheets can be welded and thermal cut at room temperature without pre-heating, all common welding and cutting processes can be used.

Appropriate health and safety precautions must be taken when welding, cutting, grinding or otherwise working on this product. Grinding, especially of primer coated plates, may produce dust with a high particle concentration.



The UK English version of this document shall prevail in case of discrepancy. Download the latest version of this document at www.ssab.com
Hardox, Strenx, Docol, Dogal, Domex, Toolox, Laser, Armox, Ramor, GreenCoat are trademarks of SSAB Technology AB, Sweden